

www.eska.com



## Eska®mono black

Technical properties and specifications



## **TECHNICAL PROPERTIES (INDICATION)**

CALIPER According to ISO 534	GRAMMAGE According to ISO 536	DYNAMIC STIFFNESS According to ISO 5629		BURSTING STRENGTH According to ISO 2759		COBB60 According to ISO 535	
mm / inches*	g/m²	<b>MD</b> mNm	<b>CD</b> mNm	<b>top</b> kPa	<b>bottom</b> kPa	max top g/m²/60sec	max bottom g/m²/60sec
1.00 / 0.040"	675	355	170	725	870		50
1.20 / 0.047"	785	495	235	780	920		50
1.50 / 0.060"	975	820	395	870	1005		50
1.70 / 0.067"	1075	1145	560	930	1055		50
2.00 / 0.080"	1275	1890	935	1015	1140		50

<sup>\*</sup>Eska®mono black is produced in mm; the inches in the list are not exact conversions of the calipers in mm, but the closest US equivalent.

	SPECIFICATIONS	UNITS	TOLERANCES		TEST METHODS
CALIPER	See above	mm / inches	< 1.5 mm / 0.060" ≥ 1.5 mm / 0.060"	± 0.05 mm / ± 0.0020" (pallet average) ± 3% (pallet average)	ISO 534
SIZE		mm / inches	Sheets Rotary cut Die cut	± 1 mm / ± 0.039" ± 0.25 mm / ± 0.010" ± 0.2 mm / ± 0.008"	
FLATNESS	0	%	Convex	CD max. 1.5% MD max. 1.0%	Eska
			Concave	CD max. 1.0% MD max. 1.0%	
			S-shape	CD - sheets < 1 m / 39,4": max. 3 mm / 0,12" - sheets ≥ 1 m / 39,4": max. 5 mm / 0.20" MD max. 3 mm / 0.12"	
MOISTURE CONTENT	8.0% abs.	%	-1.5 % / +1.0%	(pallet average)	ISO 287

## **PRODUCT CERTIFICATES**

- FSC® certified (FSC-C022653)
- PEFC certified (PEFC/30-32-541)
- EN-71-part 3, Migration of certain elements (Toy Safety)
- Foodstuffs and Consumer Act (Food Safety)

## **SIZES**

- Large sheets are available in any size from 500 x 500 mm (19 11/16 x 19 11/16") to 1200 x 1600 mm (47 1/4 x 63")
- Rotary cut sizes are available in any size from 100 x 150 mm (3 15/16 x 5 29/32") to 480 x 1360 mm (18 29/32 x 53 9/16")
- Die cut sizes are available in any size from 100 x 150 mm (3 15/16 x 5 29/32") to 720 x 1050 mm (28 11/32 x 41 11/32")